

# SPECIFICATION DATABASE

GCP10 - 8/24 - V1.0



## Centre Pane 'u' Value - 6.8mm/6mm Annealed (1 x T+)



### 33.2 (16 Argon 90) 6

Coating: PLANITHERM TOTAL+ FG #5

Computed by: Oli Pringle

Computed on: 08/08/2024

Product catalog: United Kingdom

Norms: EN41 0 (201 1-04)

#### Glazing type

**Glazing 1**  
 PLANICLEAR (3mm) - Annealed  
 PVB STANDARD (0.76mm)  
 PLANICLEAR (3mm) - Annealed

---

**Cavity 1**  
 Argon 90% 16 mm

---

**Glazing 2**  
 PLANITHERM TOTAL+ FG  
 PLANICLEAR (6mm) - Annealed

#### Simulated performance datas

|  |                      |
|--|----------------------|
| Luminous Factors   | CIE (15-2004)        |
| Light Transmittance (TL)   | 78%                  |
| Outdoor Reflectance (RLe)  | 13%                  |
| Indoor Reflectance (RLi)   | 13%                  |
| Energy Factors   | EN41 0 (201 1-04)    |
| Transmittance (TE)   | 57%                  |
| Outdoor Reflectance (Ree)  | 17%                  |
| Indoor Reflectance (Rei)   | 20%                  |
| Absorptance A1 (AE1)   | 16%                  |
| Absorptance A2 (AE2)   | 10%                  |
| Solar Factors  | EN41 0 (201 1-04)    |
| Solar Factor (g)   | 0.66                 |
| Shading Coefficient (SC)   | 0.75                 |
| Thermal Transmission   | EN673-201 1          |
| Ug   | 1.2 W/(m2.K)         |
| Angle relative to the vertical   | 0°                   |
| Acoustics  | EN 12758             |
| <i>Acoustic simulated values</i>   |                      |
| Rw (C;Ctr)   | 37 (-2; -6) dB       |
| Ra   | 35 dB                |
| Ra,tr  | 31 dB                |
| STC (ASTM E41 3)   | 37                   |
| OITC (ASTM E1332)  | 29                   |
| Color Rendering  | CIE (15-2004)        |
| Transmission (Ra)  | 98.4                 |
| Reflection (Ra)  | 91.8                 |
| Safety Class   | EN 12600             |
| Pendulum Body Resistance   | 1 B1/NPD             |
| Anti-Burglary  | EN 356               |
| Burglar Resistance   | P1A/NPD              |
| Manufacturing Sizes  |                      |
| Nominal Thickness  | 28.8 mm              |
| Weight   | 31 kg/m <sup>2</sup> |
| Sustainability   |                      |
| Carbon footprint   |                      |
| <i>The value is calculated regarding the composition computed based on the standard EN 15804+ A2 (201 9)</i> |                      |
| Global Warming Potential (GWP) – A1-A3   | EN 15804+ A2 (201 9) |
| (kg. CO <sub>2</sub> eq./m <sup>2</sup> ) European average   | 52                   |



Verified Results  
 EN 410  
 EN 673

www.tuv.com  
 ID: 000036659

Calumen® calculates the photometric characteristics and thermal transmission of glass using calculation algorithms which comply with the following standards: the European standards EN 410 and EN 673, the international standard ISO9050, the Japanese standard JIS R 31 06/31 07 and the Korean standard KS L 251 4/2525. The functional output and calculation rules of Calumen® for standards EN 41 0 and EN 673 have been validated by TUV Rheinland (report 8921 2153-01). The technical performances obtained according to these standards are provided for information only and are subject to amendment.

Only the values entered in the performance declaration available on the CE marking site of Saint-Gobain Glass are official.

The sound attenuation indices are measured under laboratory conditions according to the standards EN ISO 101 40 and EN 12758. The calculated indices are provided for information only. The accuracy for Rw index lies within a range of + /-2dB. The glass thickness calculations comply with the 201 2 version of the DTU39-P4 description. The USER is responsible for ensuring that the correct calculation hypotheses are entered and the DTU39 is applied appropriately for the project concerned.